Static Shielding Bag 1900 / 1910 Series

This transparent metal-in static shielding bag is designed to provide static safe packaging for the shipment and/or storage of ESD sensitive items including outside ESD protected areas. Bags are printed with an ESD protective symbol and a lot code for traceability. Open top (1900) and ZipTop (1910) styles are available. The bags are heat sealable.

SCS Metal-In Static Shielding Bags 1900/1910 are manufactured from a polyester, metal, polyethylene laminate. The polyester dielectric in concert with the metal layer provides discharge shielding. The exterior being static dissipative allows electrostatic charges to be removed when grounded.

Open Top Bag Zip Top Bag SCS SCS SEAL Static Shielding Bag Static Shielding Bad 1900 1910 RoHS RoHS LENGTH LENGTH StaticControl.com StaticControl.com LOT 73682586721138 LOT 74632738051941 FOLD WIDTH WIDTH


Tolerance (inches): Width -0, +0.250 Length +/- 0.125 Offset 0 to 0.250 Seal width +/- 0.125

250 Note: Standard bag markings shown above and are not to scale. Bag markings are centered regardless of bag size.

OFFSET

SEAL

FOLD



RoHS 3, REACH, and Conflict Minerals Statement
None of the RoHS 3 restricted materials or REACH substances of very high concern as
of 2017/07/07, or Conflict Minerals are intentionally added in manufacturing this product.
Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE.
See SCS Warranty, Limitation of Liability and Remedies





Physical	Typical Value	Testing Method
Tensile Strength	5100 PSI, 35 MPa	ASTM D882
Puncture Resistance	12 lbs, 53 N	MIL-STD-3010C Method 2065
Seal Strength	9 lbs, 40 N	ASTM D882
Thickness	2.8 mils, .071 mm +/-10%	MIL-STD-3010C Method 1003
Marking Adhesion	Pass	IPC-TM-650 2.4.1
Transparency	40%	Tobias
Electrical	Typical Value	Testing Method
Discharge Shielding	<10 nJ	ANSI/ESD STM11.31
Surface Resistance - Interior	1x10 ⁴ to <1x10 ¹¹ ohms	ANSI/ESD STM11.11
Surface Resistance - Exterior	<1x10 ¹¹ ohms	ANSI/ESD STM11.11
Cleanliness	Typical Value	Testing Method
Silicone	Not Detected	FTIR
Heat Sealing Conditions	Typical Value	
Temperature	375°F, 190°C	
Time	0.5 - 3.5 seconds	
Pressure	30 - 70 PSI, 206 - 482 KPa	

This product is intended for commercial use only. This product is not on the Qualified Product Listing under the Defense Standardization Program.



Specifications and procedures subject to change without notice.

1900 / 1910 SERIES METAL-IN STATIC SHIELDING BAG

926 JR Industrial Drive, Sanford, NC 27332 WEB SITE: StaticControl.com PHONE (919) 718-0000 DRAWING NUMBER 1900 Series DATE October 2017

SCS