

Scotcha Tape 371A

Performance Box Sealing Tape

Manufactured in an ISO 9002 certified facility

Updated: June 2003

Supersedes: June 2000

Product Description

371A is perforamance box sealing tape with a bi-axially orientated polypropylene film backing and hot melt solvent free (synthetic rubber resin adhesive). The ScotchPro[™] polypropylene backing resists splitting when subjected to rough handling and absorbs impact shock. The adhesive is specifically formulated to

provide high initial tack and shear adhesion to fibreboard.

Physical Properties

Not for specification purposes

| Adhesive Type | Pressure sensitive hot melt | |
|----------------------|--|------------|
| | solvent free (synthetic rubber resin) | |
| | / | |
| Backing | 28 micron (0.028 mm) bi- axially oriented ScotchPro™ | |
| | polypropylene | |
| Total Thickness | 50 micron | AFERA 4006 |
| | (0.050 mm) | |
| | , | |
| Colour | Transparent, brown | |
| | • | |
| Available Widths and | | |
| Lengths | Contact your local sales office | |
| Core Size (ID) | 76 mm (3") | |
| Core Size (ID) | 70 11111 (0) | |
| Storage Conditions | Store behind present stock, in a clean dry place. Temperature of 64 - 70°F (18-21°C) & 40-50% Relative Humidity are recommended. Rotate your stock. Under correct storage conditions the tape maintains its characteristics for one year (shelf life). | |

Performance Characteristics

Not for specification purposes

| Adhesion to | 4.9 N/cm | AFERA 4001 |
|---------------------|---|------------|
| Stainless Steel | | |
| Tensile Strength | 50.0 N/cm | AFERA 4004 |
| Elongation at Break | 160 % | AFERA 4005 |
| Static Shear | 5,000+ minutes | AFERA 4012 |
| Application | Best applied at room temperature onto a clean, dry, dust-free fibreboard surface. Once applied the product performs well throughout all temperatures typically encountered by packaged products in shipping and storage environments - including deep freeze. | |

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

I.A.T.D. Packaging and Reinforced Tapes

3M Italia S.p.A. – Customer Care – Via San Bovio, 1/3 – San Felice 20090 Segrate – MI – Italy

tel. nbr. ++39 02 7035 3174/3173 fax nbr. ++39 02 7035 2111

3M Scotch and ScotchPro are trademarks of the 3M Company